

HumiSeal® Stripper 1072 Technical Data Sheet

HumiSeal® Stripper 1072 dissolves cured HumiSeal® urethane coatings or HumiSeal® water-based acrylic coatings, without negatively affecting printed wiring board substrates or components. HumiSeal® Stripper 1072 is in full compliance with the RoHS Directive 2002/95/EC.

Typical Physical Properties of HumiSeal® Stripper 1072

Stripper	1072
Compatible HumiSeal® Coatings	1A20, 1A33, 2A64, 1H2O Products
Relative Evaporating Rate (BuAc=1)	0.66
Specific Gravity	0.99
Flash Point (°C) TCC	40.6
VOC (grams/litre)	957
Shelf Life, DOM	12 months
Colour	Blue

HumiSeal® Stripper 1072 is safe for use on copper, gold, silver or nickel plating, steel, brass, bronze, phenolic resins, amine cured epoxies, polyethylene, Teflon, Kel-F, neoprene, or vulcanized rubber. It will attack anhydride-cured epoxies and most silicones. It will either swell or dissolve polystyrene, vinyl, plexiglas, and acrylics.

Directions for Use

Immerse the component or printed circuit board assembly into HumiSeal® Stripper 1072. The rate at which the existing coating will dissolve will depend upon its thickness and age. Heating HumiSeal® Stripper 1072 will increase its effectiveness (Caution: do not exceed 48°C max). The use of mechanical mixers will speed up the dissolving rate. HumiSeal® Stripper 1072 can also be used to remove coating from small areas, by applying a few drops to the desired location.

After the existing coating has been removed, thoroughly wash the assembly in isopropyl alcohol, deionized water or other qualified cleaning process. If the component surface of is cloudy after washing, the removal is incomplete. The removal should be repeated for a longer time. Oven dry the assembly for a minimum of 30 minutes at 66°C prior to recoating.

Handling Precautions

HumiSeal® Stripper 1072 is flammable and the following standard safety precautions should be observed:

- Use only in well ventilated areas.
- Protective gloves and goggles should be worn.
- In case of prolonged skin contact, wash with water.
- In case of eye contact, flush with water followed by a diluted boric solution and contact physician.
- Avoid prolonged breathing of vapours.
- Unused portions of HumiSeal® products must be disposed of in compliance with applicable environmental regulations.
- Consult the Material Safety Data Sheet (MSDS/SDS) for more specific product information.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.