

## HumiSeal<sup>®</sup> UV20GEL

### High Performance Staking and Vibration Protection UV Gel

### Technical Data Sheet

HumiSeal<sup>®</sup>UV20GEL is a fast curing, non-sag thixotropic paste which cures to give a flexible urethane acrylate that bonds well to engineered plastics and metal-based substrates. In addition to the UV cure, this material has a secondary moisture cure mechanism to ensure cure in areas shadowed from UV light. HumiSeal<sup>®</sup>UV20GEL is designed for staking and vibration dampening applications, but doubles as a high-performance adhesive for general PCB bonding applications.

Applications	Features	Substrates
• PET/RPET Clamshell Bond	• RoHS & REACH Compliant	• Polycarbonate
• Plastic Bonding	• GB 33372-2020 Compliant	• PET/RPET
• Mechanical Shock Protection	• UV Fluorescing	• PVC
• Components Staking	• Fast UV Cure	• Various Metals
• Vibration Protection	• Sag Resistant / Thixotropic Paste	• PCB components
	• Shadow Area Cure	• Compatible with HumiSeal UV Curable Conformal Coatings

#### Properties of HumiSeal<sup>®</sup> UV20GEL

##### Uncured Properties

Property	Value
Solvent Content	100% Solids
Chemical Class	Acrylated Urethane
Appearance	Opaque White
Shelf Life, DOM	6 months
Density, g/mL	1.08
Viscosity*	Non-sag Thixotropic Paste
Thixotropic Index	> 5.5

\*Highly thixotropic material, will decrease in viscosity with increasing shear rate

##### Cured Properties\*\*

Property	Value
Hardness, Shore A (Initial)	10
Hardness, Shore A (10 days post cure)	60
Tensile Strength, MPa [psi]	4.8 [700]
Elongation, %	>400
Moisture Resistance	Excellent
Surface Resistivity, Ohm	$1.4 \times 10^{12}$
Volume Resistivity, Ohm*cm	$8.5 \times 10^{13}$
Dielectric Withstand Voltage (per MIL-I-46058C)	Pass @ 1500 V
Peak Operating Temperature, °C	-40 to 125
Polycarbonate Lap Shear, psi	200
PVC Lap Shear, psi	450
Glass Transition Temperature (Tg) per TMA, °C	31
Coefficient of Thermal Expansion, ppm/K, above Tg	239
Comparative Tracking Index (CTI), 3 and 5 mm thick	600 V
Flammability at 3mm***	UL 94 H-B

\*\* Values are given as typical values

\*\*\* Flammability tested in-house with 3mm thick samples coated on FR4 substrate using conditions similar to UL94 flame chamber and passed based on flame propagation rate

**Curing**

HumiSeal<sup>®</sup> UV20GEL is a highly cross-linked material. In order to achieve maximum cross-link density and physical performance, the product must be exposed to the correct spectral output.

HumiSeal<sup>®</sup>UV20GEL can be cured using arc, microwave, or LED systems. Recommended minimum dosage is given below for an H-bulb and D-bulb arc system. An LED system with wavelength of 395 nm and power > 12W can cure UV20GEL. Because of the variations possible in curing equipment type and configuration, it is strongly recommended that you contact HumiSeal Technical Support to discuss your equipment and process in detail.

HumiSeal<sup>®</sup> UV20GEL contains a reliable secondary moisture cure mechanism which will cure any shadow areas on the assembly within 7-10 days at ambient moisture.

**Table 1: UV Cure Recommendations**

*Recommendations Based on 5mm thickness*

		Dose (J/cm <sup>2</sup> )			Irradiance (W/cm <sup>2</sup> )		
		UVA	UVB	UVC	UVA	UVB	UVC
<b>Min.</b>	Arc System; H-bulb	2.6	2.6	0.75	0.50	0.50	0.10
<b>Min.</b>	Arc System; D-bulb	8.3	3.4	0.80	1.50	0.50	0.10
<b>Min.</b>	LED System; 395 nm	2.0 (395 nm)	0	0	0.18 (395 nm)	0	0
<b>Max.</b>	Arc System; H-bulb	6.0	5.8	2.0	0.90	0.90	0.30
<b>Max.</b>	Arc System; D-bulb	15.0	7.0	2.0	2.50	1.00	0.30
<b>Max.</b>	LED System; 395 nm	10	0	0	0.50	0	0

**Storage**

HumiSeal<sup>®</sup> UV20GEL should be stored in a cool, dry, and dark location at a temperature between 1°C to 25°C. Material is sensitive to moisture, UV, and visible light. Consult SDS for safe handling recommendations.

**Caution**

Application of HumiSeal<sup>®</sup> UV20GEL should be carried out in accordance with local and National Health and Safety regulations. Use only in well-ventilated areas to avoid inhalation of vapors. Do not spray, atomize or vaporize material. Avoid contact with skin and eyes.

Consult SDS prior to use.

## Contact HumiSeal<sup>®</sup>

### HumiSeal North America

201 Zeta Drive  
Pittsburgh, PA 15238  
USA  
Tel: +1 412-828-1500  
Toll Free (US only): 866-828-5470  
[sales@humiseal.com](mailto:sales@humiseal.com)

### HumiSeal Technical Center

295 University Avenue  
Westwood, MA 02090  
USA  
Tel: +1 781-332-0734  
Fax: +1 781-332-0703  
[techsupport@humiseal.com](mailto:techsupport@humiseal.com)

### HumiSeal Europe

505 Eskdale Road, IQ Winnersh  
Berkshire RG41 5TU  
UK  
Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europesales@chasecorp.com](mailto:europesales@chasecorp.com)

### HumiSeal India

J-154, M.I.D.C Bhosari  
Pune 411 026  
Maharashtra  
India  
Tel: +91 20 66308098  
[indiatechsupport@chasecorp.com](mailto:indiatechsupport@chasecorp.com)

### HumiSeal S.A.R.L

4/6 Avenue Eiffel  
78420 Carrieres-Sur-Seine  
France  
Tel: +33 (0) 1 30 09 86 86  
Fax: +33 (0) 1 30 09 86 87  
[humiseal.sarl@chasecorp.com](mailto:humiseal.sarl@chasecorp.com)

### HumiSeal Asian Support

Tel: 852-9451-6434  
Fax: 852-2413-6289  
[asiatechsupport@humiseal.com](mailto:asiatechsupport@humiseal.com)

### HumiSeal Europe Support

Tel: +44 (0)1189 442 333  
Fax: +44 (0)1189 335 799  
[europetechsupport@chasecorp.com](mailto:europetechsupport@chasecorp.com)

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.